

# ANTIBLOCK MB: HPSABF106

## Product description

The MB HPSABF106 contains erucamide and natural silica, recommended for providing antiblock properties to PE **Thin** films and to reduce the coefficient of friction between two PE films. The granular shape of this MB, being very similar to that of the polyolefin resin in terms of size and density, allows an easy mixing/dispersion with the raw materials.

#### **Specifications (Reported on CoA)**

Content natural SILICA	9-11%	M SABF
Content ERUCAMIDE	4.5-5.5%	M SABF

## Additional Typical Values

Appearance	Milky Opaque Granules	M001
Bulk Density	0.57-0.65	M003

## **Recommendations of use**

Addition levels of MB HPSABF106 depend on various factors such as thickness of the article, expected service life, presence of fillers and other additives and commonly range from1-3%. It can also be used with other polyolefins.Not to be used in cling film applications containing Polybutene. Contact us for your specific recommendation needs. **Packaging** 

MB HPSABF106 is supplied in 25 kg plastic bags on1000 kg or 1375 kg wooden pallets.

#### **Storage Conditions**

It is recommended to avoid the exposure of MB HPSABF106 to sunlight and high temperatures for longer times as this may impair the quality of the MB. Storage lifetime is 1 year.

#### Contact

Address: 19 Rue du Mercure, Zl Ben Arous 2013 Ben Arous - Tunisia. Tel : +216 71 383 675 Fax : +216 71 383 716 Email: commercial@hosta-polymers.com

Ed. 01 10/06/2015

The information contained herein is based on our current knowledge and experience. A legally binding promise of certain characteristics or suitability for a concrete individual case cannot be derived from this information. The information here is not intended to release processors and users from the responsibility of carrying out their own tests and inspections in each concrete individual case.