

SLIPMB: HPSLF103

Product description

The MB HPSLF103 contains erucamide, recommended for decreasing the coefficient of friction between two PE films

The granular shape of this MB, being very similar to that of the polyolefin resin in terms of size and density, allows an easy mixing/dispersion with the raw materials.

Specifications (Reported on CoA)

Content ERUCAMIDE	4.5-5.5%	M SLF
-------------------	----------	-------

Additional Typical Values

Appearance	Slightly yellowish transparent Granules	M001
Bulk Density	0.55-0.65	M003

Recommendations of use

Addition levels of MB HPSLF103 depend on various factors such as thickness of the article, expected service life, presence of fillers and other additives and commonly range from 1.5-3%. It can also be used as demoulding agent in injection moulding. Not recommended for films containing Polyisobutylene.

Contact us for your specific recommendation needs.

Packaging

MB HPSLF103 is supplied in plastic bags on 1000 kg or 1375 kg wooden pallets.

Storage Conditions

It is recommended to avoid the exposure of MB HPSLF103 to sunlight and high temperatures for longer times as this may impair the quality of the MB. Storage lifetime is 1 year.

Contact

Address: 19 Rue du Mercure, ZI Ben Arous
2013 Ben Arous - Tunisia.
Tel : +216 71 383 675
Fax : +216 71 383 716
Email: commercial@hosta-polymers.com