

FILLER MB: HPFIF101

Product description

The MB HPFIF101 contains a recommended submicron CaCo3 improve the opacity of the PE Film

The granular from of this MB is very similar to that of the polyolefin resin in terms of grains size.

Specifications (reported on CoA)

Content CaCO3	75 -85%	M FIF
---------------	---------	-------

Specifications'

Appearance	White Granules	M001
------------	----------------	------

Recommandations of use

Levels of addition of MB HPFIF101 depend on various factors such as the thickness of the article

The duration service expected, presence of other additives commonly vary from 1% to 5%

Contact us for your manufacturing needs.

Packaging

MB HPFIF101 is supplied in plastic bags on pallets of 1000kg or 1375kg

Storage Conditions

It is recommended to avoid exposure of the MB HPFIF101 to the rays of the sun and high temperatures for longer times as this may affect the quality of the MB .

Contact

19 Rue du Mercure, ZI Ben Arous

2013 Ben Arous - Tunisia.

Tel : +216 71 383 675

Fax : +216 71 383 716

Email: commercial@hosta-polymers.com