

TDS/SPECIFICATION SHEET

FILLER MB: HPFIRF104

Product description

The MB HPFIRF104 contains a recommended submicron CaCo3 improve the opacity of the Fiber and other raffia PP.

The granular from of this MB is very similar to that of the polyolefin resin in terms of grains size.

Specifications (reported on CoA)

| Content CaCO3 75 -85% M FIR | Content CaCO3 | 75 -85% | M FIR |
|-----------------------------|---------------|---------|-------|
|-----------------------------|---------------|---------|-------|

Specifications'

| Appearance | White Granules | M001 |
|------------|----------------|------|

Recommandations of use

Levels of addition of MB HPFRIF104 depend on various factors such as the thickness of the article

The duration service expected, presence of other additives commonly vary from 1% to 5% Contact us for your manufacturing needs.

Packaging

MB HPFIRF104 is supplied in plastic bags on pallets of 1000kg or 1375kg

Storage Conditions

It is recommended to avoid exposure of the MB HPFIRF104 to the rays of the sun and high temperatures for longer times as this may affect the quality of the MB .

Contact

19 Rue du Mercure, ZI Ben Arous

2013 Ben Arous - Tunisia.

Tel: +216 71 383 675 Fax: +216 71 383 716

Email: commercial@hosta-polymers.com

Ed. 01 22/09/2015